

HABA Planalu N & G

Rolled aluminium plates
cut to size

Planalu is a naturally hard rolled plate with good machinability and good dimensional stability. It is easy to weld, is extremely corrosion-resistant and suitable for metallic coatings.

FINISHES PLANALU N & G

Thickness	rolled EN 485-3/4
Parallelism	EN 485-3/4 ($\leq 0.2/100$)
Evenness	EN 485-3/4
Length/width	Ra3.2-6.3 cut with a precision circular saw
HABA standard tolerance	nominal size +0.8/+0.3 mm
Customer-specific tolerance	within a tolerance field of 0.4 mm

PLANALU G

is additionally low-tension annealed

TECHNICAL SPECIFICATIONS

Tensile strength R_m	255-350 (N/mm ²)
Yield strength $R_{p0.2}$	≥ 105 (N/mm ²)
typical values	140-200 (N/mm ²)
Breaking strain ($L_o = 5 d_o$) A_5	≥ 12 %
typical values	17-22%
Brinell hardness (HBS)	≥ 70
Density	2.66 kg/dm ³
E-module	~ 70.000 N/mm ²
Thermal conductivity coefficient	110-140 W/mK
Thermal expansion coefficient	$24.2 \times 10^{-6}/K$
Electrical conductivity	16-19 m/ Ω mm ²
State	H111 (soft)

INSTRUCTIONS

HABA Planalu N and G are well suited for machining. Use tools for working aluminium with a cutting speed >2000 m/min. Threads are produced favourably with thread moulders.

CHEMICAL COMPOSITION

Magnesium	Mg	4.00-4.90 %	Copper	Cu	≤ 0.10 %
Manganese	Mn	0.40-1.00 %	Titanium	Ti	≤ 0.15 %
Chromium	Cr	0.05-0.25 %	Zinc	Zn	≤ 0.25 %
Iron	Fe	≤ 0.40 %	Other elements together		≤ 0.15 %
Silicium	Si	≤ 0.40 %	Other elements individually		≤ 0.05 %

DIN Material no.	3.3547
Designation	EN AW-5083 EN AW-AMg4.5Mn0.7
Material code	AMg4.5Mn
State	H111

MATERIAL IN USE

Plant and apparatus construction
Vehicle construction
Jig manufacturing
Prototype construction
Mechanical engineering
Toolmaking and mould construction
Ship and offshore construction
Low-temperature technology

APPLICATIONS

Base plates
Rotary tables
Side walls
Foam and sample moulds

PROPERTIES

Strength in the core of thicker plates	consistent
Machinability	good
Dimensional stability	good
Weldability (WIG/MIG)	good
Weatherproofness	excellent
Seawater resistance	excellent
Contact with foodstuffs	yes
Tenacity	high
Elongation	high

SURFACE TREATMENT

Decorative anodisation	moderate
Protective anodisation	excellent
Paintwork, coating	good
Galvanic coating	good
Chemical nickel coating	excellent

We declare that our products are not suitable for any other applications and purposes, other than those specified here and do not have other product properties than those specified here.

